



Notes:

1. Longitudinal Joints Shall Be Formed, Hot Lapped & Compacted.
2. A Sloping Metal Plate Attached To The Inside Edge Of The Paver Screed Shall Bevel The Edge Of The First Asphaltic Concrete Overlay Mat. This Wedge Slopes The Typical 2 Inch Thick Overlay Mat Over A Distance Of 6 Inches.
3. An Infrared Heater Mounted On The Side Of The Paver Shall Be Used To Preheat And Soften The Previously Laid Beveled Edge When The Adjoining Mat Is Placed.
4. Joints Shall Be Compacted While The Mixture Is Hot.

ISSUED:		<b>STANDARD DETAIL</b>  <b>ASPHALTIC CONCRETE</b> <b>LONGITUDINAL JOINT DETAIL</b>		DETAIL NO.
02/2003				223
REVISED:				M-2024-001
01/2024				SHEET 1 OF 1